

# Blackwood

blackwood

Meter reading	06	07	08	09	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	
Wood Temp °C	Corrected Moisture Content for Species & Temperature																							
05	09	09	10	12	12	13	14	15	16	16	18	19	20	20										
10	09	09	10	11	12	12	13	14	16	16	17	18	19	20	20									
15	08	09	09	10	12	12	13	14	15	16	16	17	18	19	20									
20	08	09	09	10	11	12	12	13	14	15	16	16	17	18	19	20	20							
25		08	09	09	10	11	12	12	13	14	15	16	16	17	18	19	20	20						
30		08	09	09	10	11	12	12	13	14	15	16	16	17	18	19	20	20						
35			08	09	09	10	11	12	12	13	14	15	16	16	16	17	18	19	20	20				
40				08	09	09	10	11	12	12	13	14	15	16	16	16	17	18	19	20	20			
50					08	09	09	10	11	12	12	12	13	14	15	16	16	17	18	18	19	20	20	
60						08	09	09	09	10	11	12	12	13	14	14	15	16	16	17	18	19	19	
70							08	09	09	10	11	12	12	12	13	14	15	16	16	16	17	18		
80								08	09	09	10	10	11	12	12	13	13	14	15	16	16	17		
90									08	09	09	09	10	11	12	12	12	13	14	15	15	16		



© TTPB 2000

with compliments

Timber Research Unit  
 School of Architecture, University of Tasmania,  
 Locked Bag 1-324, Launceston, Tas, 7250

phone: 03 6324 3133 fax: 03 6324 3141  
 email: Timber@arch.utas.edu.au  
 web: <http://www.tastimber.tas.gov.au>