

Tasmanian Oak: *Eucalyptus delegatensis*, *E. obliqua* & *E. regnans*

Other common names: Australian Ash

The Timber Warm, dense and resilient, Tasmanian Oak is the preferred hardwood for a wide range of applications. It works extremely well and produces an excellent finish. It can be used in all forms of construction as scantlings, panelling and flooring, and can be glue-laminated to cover long spans. Veneers, plywood and engineered products are also available. It is also a popular furniture timber, and eucalypt fibre is sought after for reconstituted board and the production of high quality paper.

Tasmanian Oak is light in colour, varying from straw to reddish brown with intermediate shades of cream to pink. It is recognised for its excellent staining qualities, which allow ready matching with other timbers, finishes or furnishings.

The Resource Tasmanian Oak is the name used for three almost identical species of eucalypt hardwoods that are normally marketed collectively. *E. delegatensis* grows at higher altitudes, while *E. regnans* is found in wetter sites. *E. obliqua* has a wide distribution, occurring in wet forests but also extending into drier areas. The name Tasmanian Oak was originally used by early European timber workers who believed the eucalypts showed the same strength as English Oak.

Eucalypts are light demanding and grow best where they are not overshadowed. Regeneration occurs after fire, and seedlings establish best on bare mineral soil in the absence of leaf litter. In Tasmania, eucalypts may live for 400 years or more and regularly attain a height of 70m; some individuals have been recorded as reaching 100m. Mature trees may be 3-4m or more in diameter.





Tasmanian Oak properties:

Colour	Generally straw to light, reddish brown.
Grain	Grain is usually straight, open and even. It is occasionally coarse-grained or fiddlebacked. Growth rings are visible and usually conspicuous.
Texture	Uniform and smooth.
Durability	In-ground contact: Class 4. Outside above ground: Class 3. Termite resistance of heartwood: Not resistant. Refer to AS 5604-2005 Timber - Natural durability ratings. For exterior applications, it should be painted or coated.
Lyctid susceptibility	Sapwood is generally susceptible. Tasmanian Oak is usually sold free of sapwood.
Sizes	Dressed seasoned timber 40 to 285mm wide by 12 to 40mm thick. Undressed seasoned timber 50 to 300mm wide by 19 to 50 mm thick. Lengths up to 5400mm long are available, with the bulk of production between 2700 and 4200mm long.
Density	Approximately 700kg/m ³ at 12% moisture content. Unseasoned density approximately 1000kg/m ³ .
Shrinkage (green to 12% MC)	Approx. 5.5% radial, 11% tangential before reconditioning; 3.5% radial, 6.5% tangential after reconditioning.
Movement	Between 25% and 5% MC, radial movement is approximately 0.23% per 1% MC change; tangential movement about 0.36% per 1% MC change.
Strength groups	Seasoned SD3 and SD4, unseasoned S3 and S4.
Joint group	Seasoned JD3, unseasoned J3.
Structural grades	Most commonly available stress grades are F17 seasoned, F8 unseasoned.
Toughness (Izod)	1J3 unseasoned, 18J seasoned.
Hardness (Janka)	4.2kN unseasoned, 5.7kN seasoned.

Fire hazard properties: flooring (AS ISO 9239.1)

Critical radiant heat flux	> 2.2 and < 4.5kW/m ²
Smoke development rate	< 750%.min

Fire hazard properties: wall and ceiling lining (AS/NZ 3837)

Material group no.	3
Average extinction area	< 250m ² /kg

Workability

General	Tasmanian Oak is highly resilient and relatively easy to work.
Blunting	Moderate. Can be severe in dense material.
Sawing	Cuts fairly cleanly with moderate feeding force.
Planing	Moderate feeding forces required. Surfaces very smooth and lustrous when working with the grain.
Moulding	Surfaces are true and clean, even end grain. Holds edges well.
Boring	Easy to drill. Holes are usually clean and to size.
Rebating + mortising	Generally produces excellent results.
Turning	Turns well with sharp arrises.
Nailing	Pre-drilling is often necessary in seasoned or denser material. Nails hold well.
Gluing	Glues satisfactorily with most common adhesives.
Bending	A good to fair bending timber. 25mm material bends reasonably well to a radius of 100mm.
Finishing	Readily worked to a smooth, lustrous surface. Most finishes adhere very well. Stains very well.

for further information contact:

Locked Bag 1324, Launceston, Tasmania, 7250
 freecall in Tasmania: 1800 244 870
 other states: 03 (int+613) 6324 4470
 web: www.tastimber.tas.gov.au
 email: info@tastimber.tas.gov.au

Due to the printing process, the colours shown are indicative only.